ams AG
Tobelbader Straße 30
8141 Premstaetten
Austria

T +43 3136 500-0 F +43 3136 525-01 sensors@ams.com www.ams.com



Premstaetten, November 27, 2019

PCN20-2019 - <u>UPDATE</u>: Epoxy Change for all NanEye 2D Camera Modules & Connector

Dear Customer,

ams AG is planning to change the epoxy of the Naneye 2D camera module & connector from Epotek 320NC-2 to Epotek TJ2139-LH Black.

Change Justification and Description

During reliability testing, ams AG has observed failures in the thermal humidity test (85C/85% RH) of the camera modules. This failure does not appear on the connector. The failure mode that was observed is an open electrical contact due to corrosion in the RDL resulting in a failing functionality of the tested product. Storage under high temperature and high humidity may eventually lead to a failure of the camera modules.

The root cause investigation has shown that the current epoxy plays a major role in the RDL corrosion on the camera module due to its low glass transition temperature, therefore we want to change to the new epoxy, which has high glass transition temperature. This change is also applicable to the connector since the epoxy is used on both camera module and connector.

Risk Assessment

A risk assessment has been carried out where major risks have been identified and mitigated accordingly. Details will be shared to the customer upon request.

Impact on Product

ams AG expects that the corrosion will be addressed by this epoxy change.



Impact on Material

The bill of materials (BOM) will be updated accordingly.

Impact on Reliability

By changing the epoxy to Epotek TJ2139-LH Black, the RDL corrosion of the camera module is avoided.

Impact on Packing & Shipment

After this change, there is no more need to deliver the product in a moisture barrier bag (MBB) with desiccant.

Implementation Date and Schedule

ams AG plans to implement this change by end of December 2019 (after the qualification exercise is completed).

Traceability

The ams ERP system assures the traceability by batch ID.

The following products will be affected

| Material No | Material Description |
|-------------|-----------------------------------|
| 301170005 | NE2D_RGB_FOV90F4.0_2m FT SE |
| 301170006 | NE2D_RGB_FOV90F6.0_2m FT SE |
| 301170007 | NE2D_RGB_FOV90_F2.7_2m FT SE |
| 301170012 | NE2D_RGB_FOV90F4.0_NP _2mFT SE |
| 301170016 | NE2D_RGB_FOV90_F2.7_Stereo FT SE |
| 301170017 | NE2D_RGB_FOV90_F2.7_NB_2m FT SE |
| 301170022 | NE2D_RGB_FOV90F6.0_NB_2m FT SE |
| 301170026 | NE2D_RGB_NP_2m FT SE |
| 301170029 | NE2D_RGB_FOV90_F2.7_LEDRing FT SE |
| 301170030 | NE2D_RGB_FOV160_F2.4_2m FT SE |
| 301170037 | NE2D_RGB_FOV120_F2.8_0.4m FT SE |
| 301170039 | NE2D_RGB_FOV120_F4.0_0.5m FT SE |
| 301170041 | NE2D_RGB_FOV120_F4.0_2m FT SE |
| 301170044 | NE2D_RGB_FOV120_F4.0_1.1m FT SE |



| 301170054 | NE2D_RGB_FOV120_F2.8 SE |
|-----------|-----------------------------------|
| 301170055 | NE2D_B&W_FOV160_F2.4_2m FT SE |
| 301170061 | NE2D_RGB_FOV90_F2.7_1.78mSh FT SE |
| 301170065 | NE2D_RGB_FOV90_F2.7_0.3m FT SE |
| 301170067 | NE2D_RGB_FOV90_F2.7_1.1m FT SE |
| 301170085 | NE2D_RGB_FOV160_F2.4_3m_DP FT SE |
| 301170088 | NE2D_RGB_FOV120_F2.8_3m_DP FT SE |
| 301170089 | NE2D_RGB_FOV90F4.0_8cm FT SE |
| 301170090 | NE2D_RGB_FOV90_F2.7_3m FT SE |
| 301180003 | NE2D_B&W_FOV120_F2.8_2m FT SE |
| 301180004 | NE2D_B&W_FOV90_F4.0 FT SE |
| 301180005 | NE2D_B&W_2m FT SE |
| 301180006 | NE2D_B&W_FOV90_F2.7_NB_2m FT SE |
| 301180009 | NE2D_B&W_FOV90_F2.7_2m FT SE |
| 301180010 | NE2D_B&W_FOV90F6.0_3m FT SE |
| 301190004 | NE2D_RGB_F2.8_FOV120_SGA FT SE |
| 301190005 | NE2D_RGB_FOV90_F6.0_SGA FT SE |
| 301190011 | NE2D_RGB_F2.7_FOV90_SGA FT SE |
| 301190014 | NE2D_RGB_FOV90_F4.0_SGA FT SE |
| 301200005 | NE2D_B&W_FOV90_F4.0_SGA FT SE |
| 301200007 | NE2D_B&W_F2.7_FOV90_SGA FT SE |
| 301200008 | NE2D_B&W_F2.8_FOV120_SGA FT SE |
| 302630001 | NE2D_RGB_FOV120_F2.8_3m FT SE |

Please be advised that unless we receive your written refusal concerning this change notification within 30 days, the change notification shall be deemed accepted. If you do have further questions, please do not hesitate to contact ams at any time.

Best regards,

Peter Crabbe

ams AG

Director Operations CIS